

[54] METHOD FOR OBTAINING STRONG ADHESIVE BONDING OF COMPOSITES TO DENTIN, ENAMEL AND OTHER SUBSTRATES

[75] Inventor: Rafael L. Bowen, Gaithersburg, Md.

[73] Assignee: American Dental Association Health Foundation, Washington, D.C.

[21] Appl. No.: 516,956

[22] Filed: Jul. 25, 1983

Related U.S. Application Data

[63] Continuation-in-part of Ser. No. 457,029, Jan. 10, 1983.

[51] Int. Cl.³ A10N 1/02; A65K 5/00; C09K 3/00

[52] U.S. Cl. 523/116; 106/35; 260/998.11; 433/228; 424/147; 424/502; 523/114; 523/115

[58] Field of Search 424/147, 295; 106/35; 523/115, 116, 114; 433/228; 260/998.11

[56] References Cited

U.S. PATENT DOCUMENTS

3,200,142	8/1965	Bowen	106/35
3,635,889	1/1972	Bowen	106/35
3,785,832	1/1974	Bowen	106/35
4,001,483	1/1977	Lee et al.	526/270
4,148,988	4/1979	Masuhara et al.	106/35
4,148,988	4/1979	Masuhara et al.	106/35
4,155,890	5/1979	Hofacker-Freifrau	523/115
4,188,317	2/1980	Temin	260/998.11
4,235,633	11/1980	Tomioka et al.	260/998.11
4,251,565	2/1981	Bowen	433/226
4,302,376	11/1981	Walkowiak et al.	106/35
4,373,035	2/1983	Bowen	523/113
4,433,959	2/1984	Faunce	106/35

FOREIGN PATENT DOCUMENTS

1448134 9/1976 United Kingdom 106/35

OTHER PUBLICATIONS

Chemical Abstracts, vol. 86, No. 16, Apr. 18, 1977, p. 303, Abstract 86:111205r.

Chemical Abstracts, vol. 90, No. 8, Feb. 19, 1979, pp. 394-395, Abstract 90:61270t.

Chemical Abstracts, vol. 96, No. 16, Apr. 19, 1982, p. 463, Abstract 96:129756n.

Palit, S. R. and Koner, R. S., "Permanganate-Oxalic Acid as a Redox Initiator in Aqueous Media," 57 *J. Polymer Sci.*, 609-615, (1962).Lal et al., "New Polymerization Catalysts for Methyl Methacrylate," 24 *J. Polym. Sci.*, 75-84, (1957).Uehara, "Polymerization of Methyl Methacrylate Initiated by a Combined Action of Trichloroacetic Acid and Dimethylaniline," *Bull. Chem. Soc. Jap.*, 685-687, (1958).Hrabak et al., "The Initiation of Polymerization of Unsaturated Tertiary Amines with Carboxylic Acids," 182 *Macromol. Chem.*, 1595-1603, (1981).

Bowen, R. L., "Adhesive Bonding of Various Materials

to Hard Tooth Tissues. I. Method of Determining Bond Strength," 44 *J. Dent. Res.*, 690-695, (1965).Bowen, R. L., "Investigation of the Surfaces of Hard Tooth Tissues by a Surface Activity Test," in Phillips, R. & Ryge, G. (eds.): *Proceedings of the Workshop on Adhesive Restorative Dental Materials*, 177-191 at Indiana University, Sep. 28-29, 1961, Spencer, Indiana: Owen Litho Service.Bowen, R. L., "Development of an Adhesive Restorative Material," in *Adhesive Restorative Dental Materials II*, 225-231, University of Virginia Workshop, Public Health Service Publication No. 1494, (Washington, D.C.: U.S. Government Printing Office, 1966).Sax, N. I., *Dangerous Properties of Industrial Materials* 715, (1957), Reinhold Publishing Corporation, New York, N.Y.Dwyer, F. & Mellor, D., *Chelating Agents and Metal Chelates* 311, (1964), Academic Press, New York, N.Y.Bowen, R. L., "Adhesive Bonding of Various Materials to Hard Tooth Tissues. V. The Effect of a Surface-Active Comonomer on Adhesion to Diverse Substrates," 44 *J. Dent. Res.*, 1369-1373, (1965).Plueddemann, E., "Interfaces in Polymer Matrix Composites," *Composite Materials*, vol. 6, (1974), pp. 173-216, published by Academic Press, New York, N.Y.Jedrychowski et al., "Influence of a Ferric Chloride Mordant Solution on Resin-Dentin Retention," 60 *J. Dent. Res.*, 134-138, (1981).

(List continued on next page.)

Primary Examiner—Ronald W. Griffin

Attorney, Agent, or Firm—Allegretti, Newitt, Witcoff & McAndrews, Ltd.

[57] ABSTRACT

Materials and methods for improving the adhesion of composite materials and resins to dentin, enamel and other substrates are disclosed. Preferably, the substrate surface is treated with an aqueous solution of at least one acidic salt containing a polyvalent cation which preferably is capable of changing valence by unit steps (univalent changes) and which can bind to dentin or enamel surface sites, and at least one anion which preferably forms a relatively water-insoluble precipitate or precipitates with calcium, and which contains at least one carboxyl group and preferably two or more carboxyl groups. The resultant surface is then treated with a solvent containing a composition preferably comprising N-phenylglycine. Finally, a solution is applied which contains at least one compound selected from the group consisting of (1) the addition reaction product of pyromellitic acid dianhydride and 2-hydroxyethyl methacrylate (PMDM), (2) the addition reaction product of 3,3',4,4'-benzophenonetetracarboxylic dianhydride and 2-hydroxyethyl methacrylate (BTDA-HEMA), and (3) 4-methacryloxyethyltrimellitic anhydride (4-META). Alternative embodiments are also set forth.

27 Claims, No Drawings